



## TSS MELAMINE FACED PARTICLE BOARD



### TECHNICAL CHARACTERISTICS \*

RESISTANCE TO ABRASION	EN 14323	Printed Class 1, Unicolour Class 3A
RESISTANCE TO WATER STEAM	EN 14323	≥ Level 4
RESISTANCE TO SCRATCHES	EN 14323	≥ 1,5N
RESISTANCE TO STAINS	EN 14323	Group 1 & 2, class ≥ 4
RESISTANCE TO LIGHT	EN 14323	≥ 6 blue wool scale
RESISTANCE TO CRACKS	EN 14323	Class ≥ 3
RESISTANCE TO DRY HEAT	EN 12722	Class B
TENDENCY TO RETAIN DIRT	UNI 9300	Level ≥ 4
SURFACE DEFECTS	EN 14323	Spots: ≤2 mm <sup>2</sup> /m <sup>2</sup> Length: ≤20 mm/m <sup>2</sup>
THICKNESS VS. NOMINAL VALUE **	-	+ 0,7 +/-0,3mm



### CLEANING & MAINTENANCE

The melamine surfaces are the most resistant among those used in the furniture field. For cleaning, it is preferable to choose a detergent for domestic use. It is recommended that you avoid spraying products directly onto the surface, as this may leave stains and marks; instead, it is preferable to apply the detergent product on a soft damp cloth, clean the surface and then rinse it. Avoid using abrasive products, bleach or highly chlorinated products or acids.

In case of very light colours, the aforementioned cleaning procedure may be insufficient in order to remove the dirt from the furrows of the deep surfaces. In this case, it is recommended to delicately clean that area, by using a melamine magic sponge: wet the sponge with tepid water and squeeze it. Avoid using abrasive sponges, as they may damage the surface.

Upon request, a cleaning kit including a mild detergent and a magic sponge may be sent by CLEAF to the interested customers.

\* Values reported herein are related to a standard product configuration. For customized non-standard products, please contact our Sales Office.

\*\* The tolerance on the nominal thickness variation is guaranteed up to a maximum thickness of 25mm panel.